



**Asphalt Roofing Manufacturers Association**

1156 – 15th Street, NW, Suite 900

Washington, DC 20005

Tel: 202-207-0917

Fax: 202-223-9741

[www.asphaltroofing.org](http://www.asphaltroofing.org)

**ARMA PRODUCT BULLETIN**

**SELF-ADHESIVE MODIFIED BITUMINOUS ROOFING MEMBRANES**

Modified bituminous roof membranes continue to be popular option for low-sloped roofs due to their proven performance. Historically these products have been torch-applied, mop-applied using hot asphalt (SBS only), or applied with solvent-based adhesives. All of these conventional application methods result in excellent finished roof systems. Self-adhesive membranes combine the performance of proven modified bituminous compounds with a self-adhesive bituminous layer for ease of application.

Self-adhesive membranes are constructed in a similar fashion to traditional modified bituminous materials. Self-adhesive compounds comprise asphalt, polymers and filler; additionally certain resins may be added to improve adhesion characteristics. The membranes are reinforced with fiberglass, polyester, or a combination of the two. Products designed for exposure to the elements are typically surfaced with mineral granules or other opaque surfacing. The self-adhesive layer is protected with a release film or paper, which is removed during or just prior to the installation of the membrane. These membranes are manufactured either by using the same modified bituminous compound above and below the reinforcement, or by using an APP or SBS modified bituminous compound above the reinforcement and a bituminous self-adhesive compound below the reinforcement. Safe and fast application, environmental friendliness, and use of highly engineered polymer-modified asphalts, are among the numerous advantages of self-adhesive membranes.

There is an ASTM International standard written specifically to address self-adhesive membranes installed beneath exposed roofing materials (widely used as ice dam protection at eaves). This standard is ASTM D1970, “Standard Specification for Self-Adhering Polymer Modified Bituminous Sheet Materials Used as Steep Roofing Underlayment for Ice Dam Protection”. Work is in progress to develop new standards to address APP and SBS based self-adhesive membranes used in both steep-slope and low-slope applications. Further, the International Code Council (ICC-ES) has taken steps to revise existing acceptance criteria for roof membranes (AC-75) to include self-adhesive materials.

Manufacturers' application recommendations must be consulted before specifying or installing a particular product, but some general considerations related to the application of self-adhesive membranes include the following:

- Self-adhesive membranes are generally packaged and stored in cardboard boxes or are protected with opaque wrapping. Unprotected self-adhesive products should not be stored in direct sunlight since exposure to ultraviolet (UV) rays may affect the adhesive properties, especially on the outer convolutions of the roll. Membranes should not be used if they are not tacky to the touch.
- Roof must have adequate slope and drainage.
- When used over decks with attic spaces, ensure that the installation of the self-adhesive membrane does not prevent or interfere with the ventilation of the existing construction. Typically these materials form a vapor barrier, and if applied over warm attic spaces, adequate and thorough ventilation is needed to prevent condensation.

The following information varies significantly by manufacturer. Individual suppliers should be consulted for specific recommendations.

- At the time of installation, the air, product, and substrate temperatures should be at or above the minimum application temperature recommended by the manufacturer. Consult the specific manufacturer for recommendations for material storage and handling during colder weather application.
- The substrate must be free of any dust, dirt, oils, moisture or debris that could interfere with proper adhesion. Often the roof surface must be primed prior to membrane application - check with the manufacturer regarding requirements for primer type, application rate, and drying time.
- There is no liquid bituminous layer to fill all the surface irregularities. Consequently, proper application is essential, especially at all overlaps and T-joints. End laps on the mineral-surfaced sheets may need to be heat welded or sealed with compatible roofing mastics.

Although self-adhesive modified bituminous membranes are not new, they are being used in many new applications, and when specified and installed properly, they provide an excellent roofing option.

**Note:** These recommendations were prepared by and have the approval of the Asphalt Roofing Manufacturers Association for informational purposes only. They are not intended to revoke or change the requirements or specifications of the individual roofing material manufacturers or local, state and federal building officials that have jurisdiction in your area. Any question, or inquiry, as to the requirements, or specifications of a manufacturer, should be directed to the roofing manufacturer concerned.

May 5, 2004